



MAXURETHANE®

INJECTION MONO

ONE-COMPONENT POLYURETHANE INJECTION RESIN FOR STOPPING WATER LEAKS AND SOIL CONSOLIDATION



DESCRIPTION

MAXURETHANE® INJECTION MONO is one-component, 100% solids, solvent-free polyurethane-based injection resin which react quickly with water to produce a semi rigid waterproofing foam which expands up to 15 times its initial volume.

MAXURETHANE® INJECTION MONO is a water reactive, non hydrophilic but hydrophobic resin, thus the resulting foam does not absorb water and will not be affected by water dryness: it will not shrink or swell. The gel time of the product is adjustable by adding a certain percentage of **MAXURETHANE® INJECTION MONO CAT** catalyst.

APPLICATION FIELDS

- Water cut-off, sealing and filling of cracks and fissures into wet substrates or subjected to high hydrostatic pressure conditions with running water leaks for:
 - Damaged, cracked or honeycombed concrete.
 - Stone or brick masonry.
 - Below grade structures: tunnels, galleries, basements, retaining walls, foundations, etc.
 - Pipe network and retaining structures of drinking water: dams, water tanks, channels, swimming pools, reservoirs, etc.
 - Sewer system: sewers, manholes, utility boxes, waste water tanks, etc.
- Sealing and filling of construction or expansion joints in concrete structures.
- Plugging of running water leaks.

- Filling of large cavernous spaces, voids and cracks in stone substrates or concrete structures.
- Consolidation and stabilization of soils.

ADVANTAGES

- Easy to use. Just requires one-component injection equipments.
- Hydrophobic system: reacts with the flowing water or humidity present in the substrate. No water injection is required.
- Low viscosity, even during injection process which ensures a good and deep penetration into the substrate.
- High expanding ratio, up to 15 times its original volume.
- High dimensional stability once cured. Does not shrink or swelling by dry/wet cycles.
- High chemical stability with long lasting and high mechanical strengths. Withstands high hydrostatic pressure.
- Solvent-free. Environmentally friendly.
- Gel time adjustable depending on the amount of catalyst **MAXURETHANE® INJECTION MONO CAT** added to resin.

APPLICATION INSTRUCTIONS

For additional information, consult the Technical Dossier for injection procedure detailed in the "**MAXURETHANE® INJECTION System**".

Mixing

Pour **MAXURETHANE® INJECTION MONO** in a clean and dry container and then add the catalyst from 2% to 10% by weight. If critical high pressure water intrusions are present, **MAXURETHANE® INJECTION** must react immediately when it

comes in contact with water, thus in order to accelerate the reaction rate, a 10% of catalyst must be used. On the opposite, a slightly catalysed product, i.e. 2%, will assure a good penetration when very fine capillary cracks are injected. Check previously the proper catalyst ratio depending on job-site conditions and reaction time desired.

Application

Resin injection: Since **MAXURETHANE® INJECTION MONO** does not require water or it reacts with the moisture existing in the substrate to be injected, the system is suitable for one component injection equipment. Hydrophobic resins, such as **MAXURETHANE® INJECTION MONO** do not need large amounts of water for the reaction unlike hydrophilic materials, so a simultaneous injection of water is not necessary. Only if the area of application seems to be dry, pre-injection of water is recommended.

It is essential to keep the equipment absolutely dry. Prevent any moisture from coming into contact with the mixture in order to avoid a premature reaction of the product. If the reaction of the batch occurs while pumping, the injection machine must be immediately shut down and flushed with **MAXURETHANE® INJECTION CLEANER** in order to avoid built-up and clogging of the equipment.

The basic steps for the injection procedure are the followings:

1. Clean the substrate or concrete surface along the joint, crack or fissure.
2. Plan a pattern of the injection points and then, drill holes.
3. Clear the injection holes
4. Set the injection packers.
5. Clear and seal the joints or cracks with a **MAXPLUG®/MAXREST®** fast-set repair mortar (Technical Bulletins 4 and 2, respectively).
6. Inject the polyurethane-based resin **MAXURETHANE® INJECTION MONO** mixed with the catalyst **MAXURETHANE® INJECTION MONO CAT**.
7. Clean the surface, tools, mixing equipment and injection equipment of resin.

Application conditions

Both temperature and humidity of the environment must be observed because they will determine the pot life of the already mixed batch. The higher

temperature and relative humidity, the shorter is the induction time. Since **MAXURETHANE® INJECTION MONO** can react with the humidity of the air, it is advisable to prepare the mixture only immediately before the injection is about to start. Mix just the quantity that the equipment is capable to inject in a reasonable time. Nevertheless, already mixed and catalysed resin could be stored for 3-4 days in airtight containers.

Cleaning and maintenance of equipment

All tools, mixing equipment and injection pump are cleaned with **MAXURETHANE® INJECTION CLEANER** immediately after use or if works are interrupted for a long period. Once the product cures, only it can be removed with mechanical means. Circulate the cleaner through pump for several minutes. It is recommended to circulate mineral oil after the cleaner in order to displace the solvent.

CONSUMPTION

Consumption varies according with the use. A preliminary test on-site will determine the coverage exactly.

IMPORTANT INDICATIONS

- Try to inject the resin when cracks and fissures are in the maximum width of their movement cycle.
- Observe the safety precautions of the product and the injection equipment during both the handling and the resin injection process.
- Avoid premature contact of resin with water in order to avoid any reaction before injection.
- For further information and other uses not specified in this Technical Bulletin consult our Technical Department.

PACKAGING

MAXURETHANE® INJECTION MONO is supplied in 5 kg and 25 kg metallic drums.

MAXURETHANE® INJECTION MONO CAT is supplied in 5 kg and 25 kg metallic drums.

MAXURETHANE® INJECTION CLEANER is supplied in 5 l and 25 l metallic drums.

Accessories

DRIZORO® supplies injection equipment consisting of manual pumps such **DRIZORO® PUMP B1** and electric powered pumps such

MAXURETHANE® INJECTION MONO



DRIZORO® PUMP A2, as well as injection packers, pressure hoses, etc.

STORAGE

Six months in its original unopened containers in a dry and covered place, protected from humidity, direct sunlight and frost, at temperatures between 5 °C to 35 °C.

SAFETY AND HEALTH

During mixing and injection do not work without protection of safety rubber gloves, safety clothing, safety goggles and full face shields permanently. Spills and blow outs may happen due to the pump pressure. In case of skin contact, wash with abundant water and soap. If one of the

components or mixture comes in contact with the eyes, rinse immediately with clean water but do not rub. If irritation persists, seek medical assistance. If ingested, seek immediate medical assistance. Do not induce vomiting. Provide suitable ventilation in the working area. Observe the usual precautions necessary for the use and applications of this type of products.

For further information, Safety Data Sheet for **MAXURETHANE® INJECTION MONO** is available by request.

Disposal of the product and its empty packaging must be made by the final user and according to official regulations.

TECHNICAL DATA

Product Characteristics	
CE Marking, EN 1504-5	
Description. Concrete injection for swelling fitted filling cracks. U(S1)W(10)(3/4)(10/30)	
Uses: Building and civil engineering works	
Principles / Methods. Protection against ingress by filling cracks (Principle 1-PI / 1.4)	
Colour and appearance resin/ catalyst	Brown liquid/ Clear or yellowish liquid
Characteristics of components	
Colour and appearance resin/ catalyst	Brown liquid/ Clear or yellowish liquid
Solids content, DIN 53189 (%)	>99,0 ±0,1
Density resin/catalyst at 20 °C, DIN 53 217/1-2 (g/cm ³)	1,11/ 0,95 ± 0,1
Flash point resin/ catalyst (°C)	> 200/ > 100
Application and curing conditions*	
Induction time with 2% / 5% / 10% of catalyst (s)	40 / 19 / 10
Time for total reaction with 2% / 5% / 10% of catalyst (min/sec)	5-9 min / 2 min / 55 sec
Cured product characteristics*	
Expansion ratio from initial volume	10 - 15
Solubility in water	None
Shrinkage	None
Toxicity	Non-toxic cured foam, solvent-free
Chemical resistance	Resistant to most diluted acids and alkalis, ground salts and micro organisms

* Data at 20 °C and 50% R.H.

GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. **DRIZORO®**, **S.A.U.** reserves the right to introduce changes without prior notice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department. This version of bulletin replaces the previous one.



DRIZORO, S.A.U.

C/ Primavera 50-52 Parque Industrial Las Monjas
28850 TORREJON DE ARDOZ – MADRID (SPAIN)
Tel. 91 676 66 76 - 91 677 61 75 Fax. 91 675 78 13
e-mail: info@drizoro.com Web site: drizoro.com

ISO 9001
ISO 14001

BUREAU VERITAS
Certification

ES045396-1/ES045397-1

